Journal of Media Horizons
ISSN: 2710-4060 2710-4052 Volume 6, Issue 6, 2025

TOPOLOGICAL INSULATORS AND QUANTUM HALL EFFECTS: TOWARD ROBUST QUANTUM COMPUTING MATERIALS

Saeed Ahmad[*1], Muhammad Haseeb[2], Saman Shams[3], Zunaira Akhtar[4], Muhammad Zain Shabbir[5]

[*1]*Department of Physics, Abdul Wali Khan University Mardan, Pakistan*
[2]*Department of Physics , University of Agriculture Faisalabad, Punjabi 38000, Pakistan*
[3]*Gulab Devi Educational Complex, Lahore*
[4]*Minhaj University, Lahore*
[5]*University of Engineering and Technology, Lahore*

DOI:https://doi.org/10.5281/zenodo.17785550

Keywords

Article History
Received: 01 October 2025
Accepted: 10 November 2025
Published: 29 November 2025

Corresponding Author: *
Saeed Ahmad

Abstract
Topological materials have transformed condensed matter physics by introducing quantum phases protected by topological invariants rather than conventional symmetry-breaking mechanisms. Topological Insulators (TIs), Quantum Hall systems, Weyl semimetals, and topological superconductors host exotic quasiparticles – including Dirac fermions, chiral edge states, and Majorana zero modes – that enable dissipationless electronic transport and robust quantum information storage. This review synthesizes current developments in the physics, materials science, and computational discovery of topological materials. Key concepts such as spin–momentum locking, quantized Hall conductance, and topological fault tolerance are discussed. Advances in thin-film growth, ab-initio modeling, and machine learning continue to accelerate the discovery of materials suitable for next-generation quantum computation.

INTRODUCTION

The traditional classification of materials into insulators, semiconductors, and conductors has long relied on the presence or absence of a bandgap. However, the discovery of Topological Insulators (TIs) has revolutionized this paradigm by introducing a fundamentally new type of quantum phase, governed not by conventional symmetry considerations but by topological invariants, most notably the Z_2 index (Hasan & Kane, 2010; Qi & Zhang, 2011). Unlike ordinary insulators, TIs possess an insulating bulk yet host gapless, metallic surface or edge states that are protected by time-reversal symmetry (Kane & Mele, 2005).

These surface states are characterized by massless Dirac fermions, whose spins are locked perpendicular to their momentum—a phenomenon known as spin–momentum locking (Xia et al., 2009; Zhang et al., 2009; Roushan et al., 2009). This unique property suppresses 180° backscattering, enabling robust, low-dissipation electronic transport even in the presence of impurities or lattice defects (Mellnik et al., 2014). The combination of topological protection and dissipationless transport makes TIs promising platforms for next-generation spintronic devices, low-power electronic circuits, and

fault-tolerant topological qubits (Hasan & Kane, 2010; Qi & Zhang, 2011).

By linking fundamental physics with practical applications, topological insulators not only challenge our understanding of electronic phases but also open avenues for technologies that exploit robust quantum phenomena at the nanoscale (Moore, 2010; Ando, 2013).



Figure 1 Surface Dirac cone of a 3D topological insulator, illustrating spin–momentum locking on the TI surface.

Prominent TI materials include Bi_2Se_3, Bi_2Te_3, and Sb_2Te_3 (Xia et al., 2009; Zhang et al., 2009). Magnetic doping (e.g., Cr, V) or proximity to magnetic layers can break TRS and open a surface-state energy gap, enabling quantized Hall effects (Chang et al., 2013).

2. Topological Hall Effects and Quantized Transport

Transport phenomena in topological materials originate from topologically protected edge channels governed by global invariants (e.g., Chern numbers, Z_2 indices).

Table 1. Properties of Helical Surface States

Parameter	Physical Meaning	Transport Implication
Spin	Locked perpendicular to momentum k	Helical states (spin specifies direction)
Momentum k	Determines spin orientation	Suppresses 180° backscattering
Time-Reversal Symmetry	Protects surface states	Insensitivity to non-magnetic disorder

2.1 Integer and Fractional Quantum Hall Effects (QHE and FQHE)

The integer QHE (Klitzing et al., 1980) arises from Landau quantization of 2D electron gases under strong magnetic fields, yielding conductance plateaus quantized in units of:

G=e2hνG = \frac{e^2}{h} \nuG=he2ν

The fractional QHE (FQHE) (Tsui et al., 1982) emerges from strong electron–electron correlations and hosts topologically ordered states with anyonic excitations.



Figure 2: Landau level fan diagram showing quantized Hall plateaus as magnetic field increases.

2.2 Quantum Spin Hall Effect (QSHE)

The QSHE, first demonstrated in HgTe/CdTe quantum wells (König et al., 2007), is characterized by helical edge states preserved by TRS. It represents a 2D TI phase described by a Z_2 invariant.

2.3 Quantum Anomalous Hall Effect (QAHE) The Quantum Anomalous Hall Effect (QAHE) occurs without an external magnetic field, typically realized by magnetic doping of topological insulators (Chang et al., 2013). Its key features include:

Perfectly quantized Hall resistance: Hall conductance is precisely quantized in integer multiples of e2/he^2/he2/h.

Zero longitudinal resistance: Electrical current flows along the edges without dissipation.

Chiral edge states driven by intrinsic magnetization: Edge channels are unidirectional, protected by the material's internal magnetic order.

QAHE is particularly promising for precision metrology and low-power electronics.

3. Topological Superconductors and Majorana Zero Modes

Topological superconductors host Majorana Zero Modes (MZMs)—non-Abelian quasiparticles essential for fault-tolerant quantum computation.

Properties of MZMs:
non-local information encoding
immunity to local decoherence
non-Abelian braiding statistics (Nayak et al., 2008)

Key Milestones

Zero-bias conductance peaks in TI–superconductor hybrids (Xu et al., 2015)
Majorana signatures in InSb and InAs nanowires (Mourik et al., 2012)
Proof-of-concept braiding in engineered quantum circuits (Aguado, 2017)

Table 2. Comparison of Major Topological Phases

Phase	Topological Invariant	Key Feature	Application Potential
Topological Insulator	Z_2	Spin-momentum locked surface states	Spintronics, low-dissipation transport
Quantum Hall Systems	Chern number	Chiral edge states	Metrology, quantized conductance
Topological Superconductors	Z_2 (often)	Majorana zero modes	Fault-tolerant quantum computing

4. Materials Growth, Computational Modeling & AI-Driven Discovery

4.1 Molecular Beam Epitaxy (MBE)

Molecular Beam Epitaxy (MBE) enables atomic-scale precision in the growth of topological insulator (TI) thin films and heterostructures, producing surfaces of exceptional quality that are critical for exploring topological phenomena (Hsieh et al., 2009). This precise control allows:

Magnetic doping: Introducing magnetic impurities into TI films can break time-reversal symmetry, opening gaps in surface states and enabling the quantum anomalous Hall effect.

Superconducting proximity coupling: Coupling TI surfaces to superconductors induces superconductivity in the topological surface states, creating platforms to realize Majorana zero modes.

Landau level engineering: High-quality TI thin films allow the formation and manipulation of discrete Landau levels under magnetic fields, facilitating studies of quantized Hall transport.

4.2 Density Functional Theory (DFT) for Predicting New Topological Materials

Density Functional Theory (DFT) has proven to be an indispensable tool for predicting novel topological materials. Using first-principles calculations, researchers have identified hundreds of compounds, including topological insulators, Dirac and Weyl semimetals, and topological crystalline insulators (Yan & Zhang, 2012). Key techniques such as band inversion analysis, parity evaluation at time-reversal-invariant momenta, and Wannier-function-based computations enable rapid classification of materials according to their topological properties. These computational approaches not only guide experimental synthesis but also allow systematic exploration of large materials databases, accelerating the discovery of next-generation topological quantum materials.

4.3 Machine Learning in Topological Materials Discovery

Machine learning (ML) has become a powerful tool in the discovery of new topological materials. Models trained on features such as crystal symmetry, structural descriptors, and electronic band characteristics have successfully identified

thousands of candidate topological phases (Regnault et al., 2022). By leveraging large materials databases, including the Materials Project, AI-driven approaches can rapidly screen and classify compounds, significantly accelerating the identification of materials with desirable topological properties. These methods complement traditional ab-initio calculations, providing a high-throughput route to discovering novel topological insulators, semimetals, and superconductors.
Machine learning models are trained on:

Crystal symmetry
Structural descriptors
Electronic band features

5. Conclusion

Topological Insulators, Quantum Hall systems, and Majorana-hosting superconductors represent a revolutionary class of materials with profound implications for electronics and quantum technologies. Their quantized transport, spin-momentum-locked surface states, and fault-tolerant quasiparticles provide a robust foundation for next-generation computing architectures.

Future breakthroughs depend on synergistic progress in:
thin-film synthesis (MBE, ALD, PLD)
ab-initio theory and DFT simulations
machine learning–accelerated materials discovery
scalable device integration
As quantum technology advances, topological materials are increasingly recognized as essential building blocks for robust, fault-tolerant quantum computation.

REFERENCES

Ando, Y. (2013). Topological insulator materials. Journal of the Physical Society of Japan, 82, 102001.

Bernevig, B. A., & Hughes, T. L. (2013). Topological insulators and topological superconductors. Princeton University Press.

Chang, C.-Z., et al. (2013). Experimental observation of the quantum anomalous Hall effect in a magnetic topological insulator. Science, 340, 167–170.

Datta, S. (2005). Quantum transport: Atom to transistor. Cambridge University Press.

Fu, L., Kane, C. L., & Mele, E. J. (2007). Topological insulators in three dimensions. Physical Review Letters, 98, 106803.

Goerbig, M. O. (2011). Electronic properties of graphene in a strong magnetic field. Reviews of Modern Physics, 83, 1193–1243.

Hasan, M. Z., & Kane, C. L. (2010). Colloquium: Topological insulators. Reviews of Modern Physics, 82, 3045–3067.

Hsieh, D., et al. (2008). A topological Dirac insulator in a quantum spin Hall phase. Nature, 452, 970–974.

Kane, C. L., & Mele, E. J. (2005). Quantum spin Hall effect in graphene. Physical Review Letters, 95, 226801.

Klitzing, K. von, Dorda, G., & Pepper, M. (1980). New method for high-accuracy determination of the fine structure constant based on quantized Hall resistance. Physical Review Letters, 45, 494–497.

König, M., et al. (2007). Quantum spin Hall insulator state in HgTe quantum wells. Science, 318, 766–770.

Landau, L. D. (1930). Diamagnetism of metals. Zeitschrift für Physik, 64, 629–637.

Laughlin, R. B. (1983). Anomalous quantum Hall effect: An incompressible quantum fluid with fractionally charged excitations. Physical Review Letters, 50, 1395–1398.

Mellnik, A. R., et al. (2014). Spin–transfer torque generated by a topological insulator. Nature, 511, 449–451.

Moore, J. E. (2010). The birth of topological insulators. Nature, 464, 194–198.

Nakahara, M. (2003). Geometry, topology and physics (2nd ed.). CRC Press.

Qi, X.-L., & Zhang, S.-C. (2011). Topological insulators and superconductors. Reviews of Modern Physics, 83, 1057–1110.

Roushan, P., et al. (2009). Topological surface states protected from backscattering. Nature, 460, 1106–1109.

Stormer, H. L., Tsui, D. C., & Gossard, A. C. (1999). The fractional quantum Hall effect. Reviews of Modern Physics, 71, S298–S305.

Tong, D. (2016). Lectures on the Quantum Hall Effect. University of Cambridge Lecture Notes.

Tsui, D. C., Stormer, H. L., & Gossard, A. C. (1982). Two-dimensional magnetotransport in the extreme quantum limit. Physical Review Letters, 48, 1559–1562.

Xia, Y., et al. (2009). Observation of a large-gap topological-insulator class with a single Dirac cone on the surface. Nature Physics, 5, 398–402.

Zhang, H., et al. (2009). Topological insulators in Bi_2Se_3, Bi_2Te_3, and Sb_2Te_3 with a single Dirac cone on the surface. Nature Physics, 5, 438–442.

Zhang, Y., Tan, Y.-W., Stormer, H. L., & Kim, P. (2005). Experimental observation of the quantum Hall effect and Berry's phase in graphene. Nature, 438, 201–204.